

**PRODUCT INFORMATION SHEET**

<b>MINERALOGICAL COMPOSITION:</b>	<b>Wollastonite</b>
<b>PACKAGING:</b>	<b>1t bulk bags; 25kg bags</b>
<b>CHEMICAL ANALYSIS:</b>	<b>TYPICAL VALUES (%)</b>
<b>SiO<sub>2</sub></b>	<b>49 - 53</b>
<b>CaO</b>	<b>44 - 48</b>
<b>MgO</b>	<b>0.45</b>
<b>Al<sub>2</sub>O<sub>3</sub></b>	<b>&lt; 0.3</b>
<b>Fe<sub>2</sub>O<sub>3</sub></b>	<b>&lt; 0.3</b>
<b>TiO<sub>2</sub></b>	<b>Traces</b>
<b>MnO</b>	<b>&lt; 0.05</b>
<b>K<sub>2</sub>O</b>	<b>0.15</b>
<b>Na<sub>2</sub>O</b>	<b>&lt; 0.03</b>
<b>Loss on Ignition</b>	<b>1.5 – 3.0</b>
<b>Average Aspect Ratio</b>	<b>1 : 6</b>

**PARTICLE SIZE:**

Produced to order

**DISCLAIMER:** The information contained in the Product Information Sheet is supplied for guidance only and is typical from numerous measurements. It does not relate to the usage of the material in combination with any other material or in any other process. No guarantee is given or implied. In no event is Hidrox Namibia Mineral Processors liable for any consequential damages.